

Sabaplast 70 T

SABA, a strong bond	Description Sabaplast 70 T is a one- or two-component polyurethane adhesive based on flammable solvents for the bonding of soft PVC foils. Sabaplast 70 T is especially appropriate for water resistant bondings.						
Solvent based adhesives	Special properties Plasticizer resistant Soft bond line High temperature resistance 						
MSP sealants	- Water resistant - Transparent						
Water based adhesives	Method of use Apply by brush. Clean surface eventually with SABA Cleaner 21. Bond both						
Silicone sealants	parts, assemble parts within 10 minutes and press well. Mix adhesive eventually with 5 weight percents SABA Vulk L for improved water resistance and temperature resistance.						
Foam coatings	Technical data Viscosity at 23 °C : approx. 2500 mPa.s						
Hotmelts	Density Solids conte Open time	ent	: approx. 880 kg/m ³ : approx. 20% : two-sidedly up to 10 minutes				
Epoxy products	Curing time:approx. 24 hoursCoverage:approx. 200 g/m²Clean with:SABA Cleaner 21						
PU products	Work temperature:minimum + 15 °C (R.H. not above 70%)Storage temperature:minimum + 5 °C and maximum + 35 °CTemperature resistance:one-component approx. + 60 °Ctwo-component approx. + 85 °C						
Polysulfide products	Shelf life : 12 months in unopened packing						
Dimm	Order information						
Primers	Packing	100 ml tin with	250 ml tin with cap	1 litre can with cover	can with	30 litres can with	200 litres drum
Cleaning agents	Contonto	brush	and brush		cap	cap	470 1.5
	Contents				5 kg	25 kg	176 kg
ColournaturalArticle No.100138							

Safety indications

See the corresponding material safety data sheet.



SABA Dinxperlo BV

Industriestraat 3, NL-7091 DC Dinxperlo, PO Box 3, NL-7090 AA Dinxperlo, the Netherlands, Tel +31 (0) 315 658999, Fax +31 (0) 315 653207, E-mail info@saba.nl, Internet www.saba.nl.

Our recommendations and instructions for use are based on the present status of know-how and technique. Clients and users should evaluate our products by themselves, with regard to utilization and requirements of their own choice. We shall take no responsibility in case our products are not being used subject to our recommendations and/or instructions for use. Furthermore, General Terms and Conditions of the Dutch Association "Nederlandse Vereniging van Rubber en Kunststoffabrikanten of January 1, 1992", will apply to our recommendations, instructions for use and the delivery of our products. Version number: 2006/03