



Technical data

Wall protection 300 gram/m²

Data	Normsn	Units	Nominal values
Material			Polyester (PES)
Thickness		mm	ca. 2.8
Colour			grey
Weight	DIN 53854	gr/m ²	300 ± 10%
Tensile strength K/l	DIN 53857	kN/m	≥ 7 / 11
Elongation at break K/l	DIN 53857	%	≥ 60 / 60
Puncture resistance	DIN 54307	N	≥ 1100
Melting point		° C	250

Wall protection 500 gram/m²

Data	Normsn	Units	Nominal values
Material			Polyester (PES)
Thickness		mm	ca. 3.9
Colour			grey
Weight	DIN 53854	gr/m ²	500 ± 10%
Tensile strength K/l	DIN 53857	kN/m	≥ 11 / 18
Elongation at break K/l	DIN 53857	%	≥ 85 / 70
Puncture resistance	DIN 54307	N	≥ 2200
Melting point		° C	250